

Designación / Designation: **Electrolytic Zinc ingots of nominal 99.995% purity in accordance with UNE-EN 1179 Grade Z1.**

VALORES MEDIOS CALCULADOS SOBRE VALORES INDIVIDUALES DENTRO DE NORMA

H = Horno Average values calculated on individual values complying with standard

T = Turno COMPOSICIÓN QUÍMICA / COMPOSITION CHIMIQUE

S = Serie ANÁLISIS DE IMPUREZAS % - Analysis of impurities IMPURITIES

Peso	H	T	S	Pb %	Cd %	Fe %	Sn %	Cu %	Al %	Ni %	not to exceed
960	6	3	315	0,001	0,0001	0,0005	0,0001	0,0002	0,0001	0,0001	0.005
970	6	3	317	0,001	0,0001	0,0005	0,0001	0,0002	0,0001	0,0001	0.005
962	6	3	319	0,001	0,0001	0,0005	0,0001	0,0002	0,0001	0,0001	0.005
952	7	1	107	0,001	0,0002	0,0001	0,0001	0,0003	0,0001	0,0001	0.005
965	7	3	340	0,001	0,0001	0,0001	0,0001	0,0002	0,0001	0,0001	0.005
962	7	3	342	0,001	0,0001	0,0001	0,0001	0,0002	0,0001	0,0001	0.005
954	7	3	344	0,001	0,0001	0,0001	0,0001	0,0002	0,0001	0,0001	0.005
947	7	3	357	0,001	0,0001	0,0001	0,0001	0,0002	0,0001	0,0001	0.005